

SILPAK R-2230

Clear Platinum Base Addition Cure RTV

R-2230 A/B—35 A Shore Clear Platinum Base (Addition Cure), two-component, room temperature curing (RTV) silicone rubber. The controlled coefficient of thermal expansion makes it ideal for casting pressure pads or to be used as an advanced composite tooling rubber. R-2230 A/B RTV is great for mold tooling where precise parting lines need to be cut or to use as a visual aid for injecting resin. Use for mold making, embedding, electrical applications, thermal expanding tools, and clear part fabrication. Use molds to cast polyester, urethane, epoxy, low melt metal (600°F), thermoplastics (Polyvinyl), wax, soap, plaster, and any material where a release free casting is required.

Features

- Room temperature curing (RTV)
- Controlled Coefficient of Thermal Expansion
- Clear

Applications

Use for mold making, embedding, electrical applications, thermal expanding tools, and clear part fabrication. Use mold for any material where a release free casting is required:

- Polyester
- Urethane
- Epoxy
- Soap
- Low melt metal (600°F)
- Thermoplastics (polyvinyl)
- Wax
- Plaster

Physical and Handling Properties

Property	Value
Color	Clear Base / Clear Activator
Mix Ratio, by weight	10 Base : 1 Activator
Mix ratio by volume	10 Base : 1 Activator
Initial Viscosity, Base, cP	
Initial Viscosity, Activator, cP	
Initial Mixed Viscosity, at 77°F, cP	35,000
Hardness, Shore A	35
Gel Time, min	
Demold Time, hours	
Specific Gravity	1.08
Tensile Strength, psi	650
Elongation, %	350
Tear Strength, pli	85
Shrinkage, in/in	
Thermal Conductivity BTU-FT F	8.0×10^{-2}
Coefficient of Thermal Expansion in F	11.0×10^{-4}

Values listed above are typical and not intended for use in specifications.

**Mixing**

The base and activator are mixed just before using. **Part B should be shaken prior to use.** Carefully weigh Part A and Part B by appropriate Mix Ratio. Automatic mixing equipment or manual mixing may be used to combine base and curing agent. Since material is clear, a double mix—mixing in one container then transferring to another and re-mixing—is recommended to ensure a thorough mix. De-airing (degassing) material is always recommended.

Curing

Immediately after mixing, place the material in a vacuum chamber to remove trapped air and allow enough room for expansion as vacuum is drawn, as much as four times its original volume. Remove from vacuum chamber and pour very gently into cavity so as not to re-incorporate air into the material. Pressure casting (50-60 psi) until cured has proven well in eliminating air bubbles. After the mold (or part) has been removed from the master, it should be left for 24 hours in order to develop its maximum mechanical strength.

Inhibition

Certain materials will cause inhibition or neutralizing of the activator. These materials are sulfur and organo-metallic salt containing compounds found in organic rubbers and many condensation cure RTVs, chloride solvents – amines. Avoid using latex gloves, water-based clays and Tin/Condensation cured RTVs. Inhibition may easily be determined by brushing a small quantity of this material over the surface and allowing it to cure. If material remains tacky and gummy after the curing time, then the part's surface is acting as an inhibitor. **See Addition Cure Technical Data Sheet for inhibiting materials.

Curing Chart

TEMPERATURE	POT LIFE	CURE TIME
100 F	30 MIN	2 HOURS
150 F	10 MIN	30 MIN
300 F	----	5 MIN

Storage & Shelf Life

Base and Activator must be stored in their original, unopened containers at temperatures between 60-90F. Shelf life of materials when kept in unopened, sealed containers, at the recommended storage conditions, is 6 months.

DISCLAIMER: the information and data contained herein are based on information we believe is reliable. Each user of the material should thoroughly test application and independently conclude satisfactory performance before commercializing. Suggestions of uses should not be taken as inducements to infringe on any patent. Silpak or Polytek Development Corp make no warranty expressed or implied, including warranties of merchantability or fitness for a particular use. Under no circumstances will Silpak or Polytek Development Corp. be liable for incidental, consequential or other damages, alleged negligence, breach of warranty, strict liability, tort, or any other legal theory arising out of the use or handling of this product.

